



Methoden-Name: ASTM D 1056 compression deflection

LOG-Name: Result-Compression

Serie 1 -

Probennummer	Prüfdatum	Durchmesser	Querschnitt	h (Dicke)	F 25%	Cd 25%	F 50%	Cd 50%	
		d0 (mm)	S0 (mm ²)	t (mm)	3. Zyklus (N)	kPa	6. Zyklus (N)	kPa	
1	050216-6	05-02-2016	39.80	1244.10	19.56	35.55	28.57	103.64	83.30

